


- CLADDING
- WINDOWS
- STREET FURNITURE

Scientific Name: Trattinnickia spp.

Family: Burseraceae

Origin: South America



Intensely Thermally Modified Product:

Minimum Average Density (20/65) [kg/m3]	453
Durability Class	I
Modulus of rupture (MOR) [MPa]	36,8 (6,8)*
Modulus of elasticity (MOE) [GPa]	7,1 (0,6)*
Compressive Strength [MPa]	37,2 (4,1)*
Static Hardness (Janka) [N]	2063,6
Tangential Shrinkage [%]	2,74
Radial Shrinkage [%]	2,99
Tangential Swelling [%]	2,57
Radial Swelling [%]	3,72

* Values in parentheses correspond to standard deviation

FSC® or PEFC certified in accordance with EUDR, UKFRC, EPBC ACT, BEL and Lacey Act



Official partner of natural fire retardant solutions



**ELEVATED
DURABILITY**

**ICONIC
CHARM**



The mark of
responsible forestry
FSC® C121009

Ask us about our Certified Products

TIMBRA by GWP
Innovating Nature Building Futures